

VeroClear

Rigid Transparent Polyjet Material

VeroClear™, a transparent PolyJet™ photopolymer, offers strength, stiffness and impact resistance ideal for concept modeling, design verification and functional testing of clear parts. VeroClear simulates PMMA (polymethyl methacrylate), commonly known as acrylic, and enables the visualization of internal components and features ideal for form and fit testing of see-through parts such as eyewear, light covers and medical devices. 3D print transparent parts, or blend with other PolyJet materials for a range of opacities, stunning hues or hardnesses, a versatility ideal for rapid prototyping. To achieve the best clarity, parts should be polished, lacquered or photo bleached.

	ASTM	Value
Tensile Strength	D-638-03	50 – 65 MPa (7,250 – 9,450 psi)
Elongation at Break	D-638-05	10 – 25%
Modulus of Elasticity	D-638-04	2,000 – 3,000 MPa (290,000 – 435,000 psi)
Flexural Strength	D-790-03	75 – 110 MPa (11,000 – 16,000 psi)
Flexural Modulus	D-790-04	2,200 – 3,200 MPa (320,000 – 465,000 psi)
HDT, °C @ 0.45MPa	D-648-06	45 – 50 °C (113 – 122 °F)
HDT, °C @ 1.82MPa	D-648-07	45 – 50 °C (113 – 122 °F)
Izod Notched Impact	D-256-06	20 – 30 J/m (0.375 – 0.562 ft-lb/inch)
Water Absorption	D-570-98 24hr	1.1 – 1.5%
Tg	DMA, E _s	52 – 54 °C (126 – 129 °F)
Shore Hardness (D)	Scale D	83 – 86
Rockwell Hardness	Scale M	73 – 76
Polymerized Density	ASTM D792	1.18 – 1.19 g/cm ³
Ash Content	USP281	0.02 – 0.06%

VeroClear

System Availability	Minimum Layer Thickness	Support Structure	Available Colors
Objet30 Pro™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
Objet30 Prime™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
Objet Eden260VS™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
Objet260/500 Connex1™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
Objet260/350/500 Connex3™	16 microns (0.0006 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
Objet1000 Plus™	16 microns (0.0006 in.)	SUP705 (WaterJet removable)	<input type="checkbox"/> Clear
Stratasys J735™/J750™	14 microns (0.00055 in.)	SUP705 (WaterJet removable) SUP706B (soluble)	<input type="checkbox"/> Clear
J4100™	27 microns (0.001 in.)	SUP705 (WaterJet removable)	<input type="checkbox"/> Clear

For information on the VeroClear material properties on the J55™, please visit www.stratasys.com/3d-printers/55.

USA - Headquarters

7665 Commerce Way
Eden Prairie, MN 55344, USA
+1 952 937 3000

EMEA

Airport Boulevard B 120
77836 Rheinmünster, Germany
+49 7229 7772 0



GET IN TOUCH.

www.stratasys.com/contact-us/locations

ISRAEL - Headquarters

1 Holtzman St., Science Park
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000

ASIA PACIFIC

7th Floor, C-BONS International Center
108 Wai Yip Street Kwun Tong Kowloon
Hong Kong, China
+ 852 3944 8888

stratasys.com

ISO 9001:2015 Certified

© 2020 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Vero, VeroClear, Objet1000 Plus, Objet30 Pro, Objet30 Prime, Objet260 Connex1, Objet500 Connex1, Objet Eden260VS, Objet260 Connex3, Objet350 Connex3, Objet500 Connex3, Stratasys J735, Stratasys J750, J4100 and PolyJet are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. MDS_PJ_VeroClear_A4_1020a

